

Ajedium™ Films -- Solef® PVDF 9009 polyvinylidene fluoride

Solef® 9009 PVDF homopolymer is a semi-crystalline fluoropolymer. Solef® film is chemically inert to most acids, aliphatic and aromatic organic compounds, chlorinated solvents and alcohols.

Solef® PVDF film has a very high purity, abrasion resistance comparable to that of polyamides and relatively low coefficient of friction. These films can be used in a wide range of temperatures and have excellent intrinsic fire resistance.

Solef® PVDF films have demonstrated excellent weathering properties and are extremely resistant to UV radiation and common industrial and environmental pollutants.

Solef® PVDF films can be used in a wide range of applications, including release films, filters, chemical resistance lining, outdoor UV resistant needs as well as electric and electronic applications.

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Features	• Homopolymer	
Appearance	• Translucent	

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.75 to 1.80		ASTM D792
Water Absorption (24 hr, 23°C)	< 0.040	%	ASTM D570

Mechanical

	Typical Value	Unit	Test method
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.15 to 0.35		
vs. Itself - Static	0.20 to 0.40		
Taber Abrasion Resistance			ASTM D4060
1000 Cycles, 1000 g, CS-10 Wheel	5.00 to 10.0	mg	
Tear Resistance - MD	8.9	cN	ASTM D1004

Films

	Typical Value	Unit	Test method
Film Thickness - Tested			
--	25	µm	
--1	50	µm	
--2	130	µm	
Secant Modulus			ASTM D882
MD	2000	MPa	
TD	2100	MPa	
Tensile Strength			ASTM D882
MD : Yield	55.0	MPa	
TD : Yield	56.0	MPa	
MD : Break	57.0	MPa	
TD : Break	54.0	MPa	

Ajedium™ Films -- Solef® PVDF 9009

polyvinylidene fluoride

Films	Typical Value	Unit	Test method
Tensile Elongation			ASTM D882
MD : Yield	6.0	%	
TD : Yield	6.2	%	
MD : Break	200	%	
TD : Break	250	%	
Dart Drop Impact	< 360	g	ASTM D1709B
Free Shrinkage (130°C)	0.70	%	ASTM D2732
Area Factor	108	ft ² /lb/mil	
Tear Propagation Resistance - MD	350	gf	ASTM D1922

Thermal	Typical Value	Unit	Test method
Glass Transition Temperature	-40.0	°C	ASTM D4065
Melting Temperature	162 to 168	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	133 to 140	°C	ASTM D3418
CLTE - Flow	1.4E-4	cm/cm/°C	ASTM D696
Specific Heat (100°C)	1600	J/kg/°C	ASTM C351
Thermal Conductivity	0.20	W/m/K	ASTM C177

Electrical	Typical Value	Unit	Test method
Surface Resistivity	> 1.0E+14	ohms	ASTM D257
Volume Resistivity	> 1.0E+14	ohms·cm	ASTM D257
Dielectric Strength (23°C, 1.00 mm)	20 to 25	kV/mm	ASTM D149
Dielectric Constant	7.50		ASTM D150

Flammability	Typical Value	Unit	Test method
Oxygen Index (3.00 mm)	44	%	ASTM D2863

Additional Information

Standard Thicknesses and Widths

- Widths are available from 22" (559 mm) to 56" (1422 mm).
- Products with widths <22 inches or >56 inches are available upon request.
- Tolerances for widths are +/- 4mm.
- For PVDF film, the standard thicknesses are 25 microns (1 mil) to 1016 microns (40 mil).

Surface Finishes

- Standard surface finish is P/M (polished / matte).
- Custom finishes of P/P (polished / polished) and M/M (matte / matte) are available.

Packaging

- Film is supplied in a roll form of high quality, cardboard core of 3" (76mm) or 6" (152mm).
- PVC cores are available upon request in 3" and 6" sizes.

Labeling

- Products are labeled to comply with national and international standards.
- Labels include product grade, unique batch number, roll length, roll width, product thickness, and net weight.

Ajedium™ Films -- Solef® PVDF 9009

polyvinylidene fluoride

Notes

Typical properties: these are not to be construed as specifications.

¹ Impact properties

² Tear properties

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2018 Solvay Specialty Polymers. All rights reserved.

